

Adhesive Nickel Bath JE303

Description

The Adhesive Nickel Bath JE303 is a pre-plating Nickel electrolyte. With the JE303 very adhesive layers, especially on hard to coat materials like stainless steel, tungsten and molybdenum can be deposited. The pH value should be kept by addition of hydrochloric acid below 1.

Risks/Disposal

The baths contains muriatic acid and nickel. The usual rules in dealing with hazardous chemicals must be complied. The specifications of the local responsible water authority are to be regarded.

Operating conditions

Voltage	2 - 6 Volt
Bath temperature	18 - 20°C
Exposure time	1 - 5 min
Anodes	Nickel
Tank material	PPH
Agitation	not necessary at short processing time

**Please note our
Safety data sheet!**

Form of delivery

- Ready to use
- Concentrate form (for bath volume > 50 liter)

Storage/Warehousing

Store closed and separated from food products and storage in convenient and special marked boxes. Do not bring in contact with cyanides or cyanide solutions, because the solutions contain hydrochloric acid